

SERTOP

PRODUCT DATA SHEET

Monolithic fresh concrete surface hardener

USES

SERTOP gives the finished concrete surface very high abrasion resistance. It is economical to use. Bonds monolithically with the surface of the fresh concrete. It is economical to use.

ADVANTAGES

-Supplied ready to use
-Easy and economical to apply
-Contains Corundum aggregate and quartz sand which gives the finished surface high abrasion resistance.

AGGREGATE CHARACTERISTICS

Aggregate type	Hardness (Mohs)
Corundum (Al ₂ O ₃) aggregate	9.0 Mohs
Quartz Sand	7.0 Mohs

DESCRIPTION

SERTOP dry shake hardener is a factory blended, quality controlled ready to use hardener in powder form. It is applied on the fresh concrete and trowelled to the surface to give a monolithic hardened surface. It is a combination of very hard natural (Corundum) aggregate and quartz sand, high quality cement and very special additives.

Corundum aggregate has a hardness of 9 Mohs and very high abrasion and wear resistance characteristics.

COLOR

Dark gray, Brick red, Green

DESIGN CRITERIA

Base concrete :

The quality of the base concrete is important and will effect the final finished surface. High quality concrete mixture must be used with a minimum 250-350 kg/m³ cement content. The water cement ratio and the concrete mix are very important too because excessive bleeding and segregation are not desirable and must be brought down to minimum level according to the weather conditions water/cement ratio, slump can vary between 60-120mm. SERTOP is a dry shake hardener therefore some moisture from the surface of the concrete is necessary to wet the powder. If there is any excess bleed water on the surface (more than necessary and needed for moisturizing the hardener) then it should be removed before applying SERTOP.

PROPERTIES

Abrasion resistance

SERTOP has high abrasion resistance. It has been tested as described in ASTM D 4060-90 and in **Böhme test** and TS 699. The tests gave an improved abrasion resistance of over 250 %

Type of coating	Average abrasion resistance Böhme test (TS 699) (cm ³ / 50 cm ²)
SERTOP	2.5

Aggregate specific gravity

The specific gravity of the aggregate is 2.98

Compressive strength

The typical 28 day compressive strength of SERTOP is 65-70 N/mm².

INSTRUCTIONS FOR USE

-Site preparation

* Finish all necessary soil compaction and floor preparation work before placing the concrete.

* Sub grade must be well drained and must be graded in uniform thickness to create uniform load bearing characteristics and eventually reduce cracks.

- Concrete placement

* Protect the working area from wind and direct sunlight. Preferably finish concreting work, after finishing roofing and wall construction.

* The concrete forms must be positioned in their correct positions one or two days before placing the Concrete, taking into consideration joint locations such as control and construction joints.

* Always use good quality concrete mix suitable for industrial floors and prepared according to internationally accepted standards.

* In industrial floors thickness of the placed fresh concrete should not be less than 10cm. unless it contains special additives to reduce thickness.

* Discharge the concrete directly from the concrete mixer truck. Deposit concrete uniformly in front of the vibrating screed.

* The grade behind the screed must be checked frequently over vibration must be avoided to stop excess fine material from coming to the surface.

* The surface is then bull floated with wood or magnesium floats.

SERTOP

PRODUCT DATA SHEET

Monolithic fresh concrete surface hardener

- Color hardener application

* When no bleed water remains on the surface of the concrete and the concrete is firm enough so that an imprint of 1.5-2 cm is made by the weight of a person. Then apply the specified amount of SERTOP dry shake hardener (as shown in table 3), spread evenly (the amount depends on outdoor or indoor use and the amount of traffic on the floor). Sertop is sprinkled on the surface and spread using a squeegee. Minimum 6 kg/m² is recommended for industrial floors. 3-5 kg/m² for pedestrian traffic but this coverage is not recommended for long lasting use.

For 10 kg/m² and more the aggregate design and the application system must be changed. If such an application is chosen then please contact our office for application and type of SERTOP hardener used.

Always comply with our application instruction details.

CLEANING

All tools should be washed with water after use.

CURING

-100-200 g/m² METOCURE curing agent should be applied to the dry cleaned concrete surface. It is manufactured to conform to ASTM C309.

-METOCURE has the advantage of preventing initial water loss from the concrete surface and eventually result in better quality and higher strength concrete. Depending on the type of curing agent used best results can be achieved if no moisture is present on the surface of concrete during the curing agent application.

STORAGE:

-Store in a dry, non humid area.
-No more than five bags should be stacked on top of each other.
-For cement based hardeners, preferably use in 6 months from production date and if properly stored this period can be as long as 1 year.

COVERAGE :

6-20 kg/m² can be used in industrial floors.

Coverage	Very Light traffic (pedestrian traffic) min 3 -5 Kg./m ²
Minimum requirement for industrial purposes is 6-7 kg/m ² . Approximately 1mm thickness is achieved for each 2 kg/m ² of hardener	Light traffic min 5 -6 Kg./m ²
	Medium traffic min 7-9 Kg./m ²
	Heavy traffic min 10-20 Kg./m ² (used under special conditions) (special mix mortar design is used)

CAUTION:

Fire

METOP EX is not flammable.

Health and safety

*It is cementitious material so do not use on floors subjected to acids and other corrosive chemicals.

*Avoid inhalation of dust while sprinkling the dry shake hardener on the surface.

*The above mentioned application system is for normal weather conditions. In the case of extreme weather conditions this application method, the concrete mixing and curing application must be modified accordingly.

* SERTOP is a cementitious material and becomes alkaline when mixed with water therefore avoid contact with skin it can be harmful and wash thoroughly with water.

LIMITED WARRANTY

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct also based on our long experience in this field of construction.

METOP LTD. Warrants it's products (SERTOP) to be free of manufacturing defects and contains best quality ingredients. Since no control is exerted over it's application and use METOP LTD. Makes no warranty, either expressed or implied, concerning this product.

Extra and special guaranties can be granted to certain big project by obtaining mutual agreements between concerning parties. The company detailed application instructions must be complied with for any company guaranties to be applicable.

METOP

INDUSTRIAL, BAHARLIYALAN 500, ACI TIC. (17), (17)

Levent-ISTANBUL/TURKEY

Tel: +90 212 294 19 00/ 91-393 81 97 Fax: +90 212 269 44 84

web: www.metop.com.tr e-mail: info@metop.com.tr

METOXON

Cluj-Napoca - Romania Tel: +40 (25) 485667 Fax: +40 (25) 595887

Bucuresti - Romania Tel: Fax: +40 (2) 2113760

www.metoxon.com - www.pardoselindustriale.ro

RIPOMET

EMIRATES

INDUSTRIAL BUILDING

RAS AL - Dubai p.o. box 189 91 Tel: +971 02 320 34 46

+971 50 736 61 80

Fax: 00 971 02 320 34 47

www.ripomet.com e-mail: info@ripomet.com

RIPOX GmbH

Steinerbrugg 11, 8230 Eschenbach, Schweiz, Switzerland

Tel: +41 (0)55 - 282 28 29 - Fax: +41 (0)55 - 282 44 58

www.ripoxgmbh.com